

COR-BAN[®] 23 ENHANCED DYE



Product description:
**CORROSION INHIBITING
COMPOUND**

FEATURES:

- ▶ A long lasting, high penetration, and water displacing corrosion inhibiting compound
- ▶ Has a stronger dye than regular **Cor-Ban[®] 23**
- ▶ May be used in the place of Airbus CML 15-006

KEY BENEFITS:

- ▶ Offers inhibition and a thin film
- ▶ Water displacing
- ▶ Very low dry film weight <0.3 mil (8 microns) required to surpass specification
- ▶ Non-cracking and non-flaking to -65°F (-54°C)
- ▶ Non-sagging, fast drying, non-tacky, and detectable film
- ▶ Solvent removable



Rev: 29123D
09-14-2021

COR-BAN® 23 ENHANCED DYE



Product description:
**CORROSION INHIBITING
COMPOUND**

KEY BENEFITS:

- ▶ Strong dye allows for easy visual detection
- ▶ > 3000 Hours Salt Spray

SPECS:

- AIMS 09-08-001 Type I Grade 3
- BAMS 565-006 Type V
- BMS 3-23J Type II Class 2 Grade A & B (QPL)
- BMS 3-35
- Fed-Ex E.O. 9-5100-7-5001

APPLICATIONS:

- ✓ Apply by conventional airless, air-operated spray equipment, or by aerosol
- ✓ Use on high profile aircraft substrates, upper edge floor beams, wheel wells, pressure deck, and center wing sections
- ✓ The **Cor-Ban® 23 Enhanced Dye** aerosol can be used in conjunction with the **Formit®** extensions to provide targeted spray to areas that may be difficult to reach but need to be coated
- ✓ All properties represented were achieved with a dry film thickness of range 0.3 - 0.5 mils (7-12 microns)
- ✓ The wet film will self level to achieve the desired dry film thickness when applied to an inclined surface
- ✓ One aerosol can covers approximately 160 ft² (14.9 m²) and one gallon of bulk material covers approximately 2290 ft² or 2290 ft²/gal (56.2 m²/liter).

COR-BAN® 23 ENHANCED DYE



Product description:

CORROSION INHIBITING COMPOUND

PHYSICAL PROPERTIES:

- ▶ **Color:** Transparent Reddish-Pink
- ▶ **Drying Time:** <1 hour
- ▶ **Exfoliation:** Pass at -65°F (-54°C)
- ▶ **Flash Point:** 114°F (46°C)
- ▶ **Low Temp Flaking:** Pass
- ▶ **Non-Volatiles:** 42%
- ▶ **Operating Temperature:** -65°F (-54°C) to 350°F (177°C)
- ▶ **Penetration:** >4 inches per hours per BMS 3-35
- ▶ **Salt Spray Protection:** >3000 hours on aluminum
- ▶ **Specific Gravity:** 0.88
- ▶ **Viscosity:** 35-40 cps.
- ▶ **Water Displacement:** 0% Rust

AVAILABLE PACK SIZES:

- ▶ Aerosol-011321]
- ▶ 5 Gallon Pail-011209]
- ▶ Special Packaging Upon Request]