

### D-5026NS



*Product description:*

### AVIONIC CORROSION PREVENTIVE COMPOUND (MIL-PRF-81309H Type II&III, Class 2) Grade CO<sub>2</sub>

#### FEATURES:

- ▶ A medium to heavy duty water displacing, thin film, corrosion preventive compound

#### KEY BENEFITS:

- ▶ Contains no ozone depleting chemicals
- ▶ Prevents corrosion and displaces water
- ▶ Provides superior protection to avionic connectors and components and has lubricating properties to prevent fretting corrosion
- ▶ Protects electrical connectors from corroding
- ▶ Protects cables, surfaces, and interior and exterior aircraft surfaces
- ▶ **D-5026NS** contains a thixotropic property to prevent it from disrupting contact between connectors
- ▶ Corrosion protection provides protection in the harshest environments
- ▶ Coating can withstand temperatures up to 105°C for only 500 hours cumulative
- ▶ Contains a film that prevents oxidation of the substrate



For more information contact us :  
[zipchem@addevmaterials.com](mailto:zipchem@addevmaterials.com)



Part of



ADDEV MATERIALS

Rev: 20065J  
09-22-2021

### D-5026NS



#### *Product description:*

### AVIONIC CORROSION PREVENTIVE COMPOUND (MIL-PRF-81309H Type II&III, Class 2) Grade CO<sub>2</sub>

#### KEY BENEFITS:

- ▶ Useful for initial protection during shipment and storage and for in-service treatment of critical areas
- ▶ The cured film can withstand temperatures as low as -55°C and as high as 85°C continuously

#### SPECS:

- Boeing Alert Service Bulletin 737-24A1148 (Called out as CIC for connectors), AD 2002-16-03 (Called out)
- DPM-5707-1 (QPD)
- Embraer E6125209 (QPD)
- Sikorsky SS 8536 Type 1 (QPD)
- MIL-PRF-81309H Type II & III, Class 2, Grade CO<sub>2</sub> (QPD)
- NSN: 8030-01-603-2129 (Aerosol) (QPD)
- NSN: 8030-01-603-2131 Type II (Aerosol) (QPD)

#### APPLICATIONS:

- ✓ Use on highly critical metal surfaces and avionic components
- ✓ **D-5026NS** can be used in conjunction with the **Formit®** extensions to provide targeted spray to areas that may be difficult to reach but need to be coated
- ✓ Store at 40°F-100°F (4°C-38°C)
- ✓ Bulk application available as **ZC-026**
- ✓ One aerosol covers approximately 140 ft<sup>2</sup>
- ✓ For removal of **D-5026NS**, use **D-5640NS**, **Sur-Prep® 3160**, or **Sur-Prep® 3167**

### D-5026NS



*Product description:*

### **AVIONIC CORROSION PREVENTIVE COMPOUND (MIL-PRF-81309H Type II&III, Class 2) Grade CO<sub>2</sub>**

---

#### **PHYSICAL PROPERTIES:**

- ▶ **Evaporation Rate:** Faster than ether
- ▶ **Flame Extension:** Flammable
- ▶ **Fungal Growth per Fed-STD-810 Method 508.7:** 0 (No Microbial Growth)
- ▶ **Outgassing per ASTM E-595**
  - **Total Mass Loss (TML):** 49%
  - **Collected Volatile Condensable Material (CVCM):** 27.3%
- ▶ **Shelf Life:** 3 years from date of shipment
- ▶ **Specific Gravity (H<sub>2</sub>O=1):** 0.86
- ▶ **Vapor Density:** Heavier than air

---

#### **AVAILABLE PACK SIZES:**

- ▶ Aerosol-007669]
- ▶ Gallons-009415]
- ▶ 5 Gallon Pail-002095]
- ▶ 55 Gallon Drum-002076]
- ▶ Special Packaging Upon Request