

Aircraft Specialty Products

AP 280

KIT

Product description:
SILICONE HEAT SINK COMPOUND
DPM 5979 QUALIFIED

FEATURES:

- ▶ A two-component kit that is comprised of uncatalyzed silicone resin and a select grade of aluminum powder that is packaged separately
 - ▶ Pre-ratioed
 - ▶ Formulated specifically for use when changing the static port heater element on DC-9 and MD-80 powerplants
-

KEY BENEFITS:

- ▶ Maintains an excellent bond
 - ▶ Exhibits vibration resistance and flexibility over a very broad temperature range from -100°F to 550°F (-73°C to 288°C) in continuous service
 - ▶ Putty-like consistency of **AP 280** exhibits a high degree of flexibility and adhesion while functioning as an excellent heat sink
-

SPECS:

- Boeing DPM 5979 (Listed on QPL)
-



Rev: 29102F
08-18-2023

 For more information contact us :
zipchem@addevmaterials.com

 Part of 

Aircraft Specialty Products

AP 280

KIT

Product description:

SILICONE HEAT SINK COMPOUND

DPM 5979 QUALIFIED

.....

APPLICATIONS:

- ✓ Once the silicon resin and aluminum powder are thoroughly mixed and applied to the substrate, **AP 280** will thicken to a "putty-like" consistency.
- ✓ Mix both components of **AP 280** completely prior to applying it to an area
- ✓ Use spatula to apply non-curing and pressure sensitive putty/aluminum mix at about 15 mils (381 microns) thick
- ✓ Let mix stand for 1 to 2 hours so that it gains "tack"
- ✓ Manipulate mix to lay heater element into putty compound

.....

PHYSICAL PROPERTIES:

- ▶ **Dielectric Constant ASTM D150:** 2.95 @ 100 Hz, 2.90 @ 100,000 Hz
- ▶ **Dielectric Strength ASTM D 149:** 900 v/mil
- ▶ **Dissipation Factor ASTM D150:** 0.004@100 Hz, 0.003 @ 100,000 Hz
- ▶ **Flash Point:** 27°C (80°F)
- ▶ **Service Temperature:** -100°F to 550°F (-73°C to 288°C) continuous
- ▶ **Shelf Life:** The un-mixed kit has a 6 month shelf-life from the date of packaging
- ▶ **Solids:** 52% prior to mixing
- ▶ **Storage Conditions:** Store in a cool, dry, and well ventilated place at a temperature between 40°F and 100°F (4°C to 38°C)

Aircraft Specialty Products

AP 280

KIT

Product description:

**SILICONE HEAT SINK COMPOUND
DPM 5979 QUALIFIED**

PHYSICAL PROPERTIES:

- ▶ **Viscosity:** 5500 cps prior to mixing
 - ▶ **Volume Resistivity ASTM D257:** 4×10^{-13} OHM-CM
-

AVAILABLE PACK SIZES:

- ▶ 1 oz (28 gram) Kit of Silicone Resin and Aluminum Powder Packaged in Separate Containers-008671
- ▶ 5 oz (142 gram) Kit of Silicone Resin and Aluminum Powder Packaged in Separate Containers-002788



For more information contact us :
zipchem@addevmaterials.com



Part of



ADDEV MATERIALS