

ZC-029



Product description:

CORROSION INHIBITING COMPOUND

FEATURES:

- A long lasting, high solids, low volatiles, high penetration, and water displacing corrosion inhibiting compound
- Non-tacky with a light amber tint

KEY BENEFITS:

- > 1500 hours salt spray on aluminum (Al)
- Fast drying and non-tacky
- Non-cracking and flaking up to -40°F (-40°C)
- Free of chromates
- Free from heavy metals
- Low toxicity

SPECS:

Boeing BMS 3-29

Page 1 of 3



- Has a detectable film
- Solvent removable
- Very low dry weight film
- High Solids > 51%

• Boeing DMS 2150 Type 1 & Type 2

Rev: 290901 05-06-2025







ZC-029



Page 2 of 3

Product description:

CORROSION INHIBITING COMPOUND

APPLICATIONS:

- ✓ Apply via airless or air-operated spray equipment
- ✓ Apply at 2-3 mils (51 to 76 microns) of wet thickness. This wet thickness can be measured with **Zip-Chem®** 's **Wet Film Thickness Gauge**.
- ✓ Aerosol application available as D-5029NS
- ✓ Use on high profile aircraft substrates
- ✓ Store **ZC-029** at 40° to 100°F (4.4°- 37.8°C) in the original unopened containers

PHYSICAL PROPERTIES:

Color: Transparent Amber

Drying Time: <12 hours</p>

► Flash Point: 122°F (50°C)

Non-Volatiles: 51% min.

Specific Gravity: 0.89

Viscosity: 140 cps.

► Water Displacement: 0% Rust







ZC-029



Page 3 of 3

Product description:

CORROSION INHIBITING COMPOUND

AVAILABLE PACK SIZES:

D-5029NS

Case of 12 of 16 fl oz (473 mL) Aerosols-002050

ZC-029

- Case of 4 each Gallon (4 each of 3.8 Liter) Cans-009422
- ▶ 5 Gallon (18.9 Liter) Pail-002109
- ▶ 55 Gallon (208 Liter) Drum-002110
- Special Packaging Upon Request

Wet Film Thickness Gauge

▶ 100266