

### COR-BAN® 35 UNDYED



Page 1 of 6

*Product description:*  
**CORROSION INHIBITING  
COMPOUND**

**FEATURES:**

- ▶ A long lasting, high solids, low volatiles, high penetration, and water displacing corrosion inhibiting compound

**KEY BENEFITS:**

- ▶ Thin, non-tacky film with a fast dry time
- ▶ Low VOC
- ▶ Free of chromates and free from heavy metals
- ▶ Low toxicity
- ▶ Non-sagging thixotropic film
- ▶ Solvent removable
- ▶ Very low dry film weight < 1 mil (25 microns) required to surpass specification
- ▶ Non-cracking and flaking to -40°F (-40°C)
- ▶ High Solids > 51%
- ▶ 2000 Hours of Salt Spray
- ▶ Offers long lasting corrosion inhibition properties



Rev: 20075M  
12-18-2025

### COR-BAN® 35 UNDYED



Page 2 of 6

### *Product description:* **CORROSION INHIBITING COMPOUND**

#### **SPECS:**

- Cessna CSNP038 Type IV B Class 2 (QPL)
- MIL-DTL-85054D (QPL)
- NSN: 8030-01-615-4738 (Undyed) 8 oz. (227 gram) Brush In Cap (QPL)
- NSN: 8030-01-615-4749 (Undyed) (QPL)
- NSN 8030-01-516-6254 (Undyed) (16 fl oz (473 mL) Aerosol (QPL))
- NSN: 8030-01-615-4751 (Undyed) Gallon (3.8 Liter) (QPL)
- NSN 8030-01-531-7364 (Undyed) 5 Gallons (18.9 Liter) (QPL)
- NSN: 8030-01-531-7362 (Undyed) Quart (946 mL) (QPL)

#### **APPLICATIONS:**

- ✓ Use on high profile aircraft substrates, such as upper edge floor beams, wheel wells, pressure deck, and center wing sections
- ✓ Apply by using conventional airless, aerosol, or air-operated spray equipment
- ✓ Apply at 1 - 1½ mils (25-38 microns) wet thickness. This wet thickness can be measured with **Zip-Chem®** 's **Wet Film Thickness Gauge**.
- ✓ The **Cor-Ban® 35 Undyed** aerosol can be used in conjunction with the **Formit®** extensions to provide targeted spray to areas that are difficult to reach but need to be coated. Please refer to the **Formit®** technical data sheet for more information.
- ✓ All properties represented were achieved with a dry film thickness of 0.5 - 0.75 mils (12-19 microns)
- ✓ One aerosol can covers approximately 95 ft² (8.8 m²)
- ✓ Cured **Zip-Chem® Cor-Ban® 35 Undyed** can be removed with **Sur-Prep® 3160, D-5640NS, ZC-640, Zip-Strip™ 125M, Sur-Prep® 3167**, or mineral spirits
- ✓ Store **Cor-Ban® 35 Undyed** at 40°F to 100°F (4.4°C - 37.8°C) in the original unopened containers. Keep containers closed when not in use and protect **Cor-Ban® 35 Undyed** from direct sunlight.

### COR-BAN® 35 UNDYED



Page 3 of 6

*Product description:*

### **CORROSION INHIBITING COMPOUND**

#### **PHYSICAL PROPERTIES:**

- ▶ **Color:** Transparent Light Yellow Tint
- ▶ **Compatibility Cd, Mg, Al:** Pass
- ▶ **Tack Free Time:** <1 hour
- ▶ **Dry Through Time:** 72 hours
- ▶ **Exfoliation:** Pass
- ▶ **Flash Point:** 115°F (46°C)
- ▶ **Low Temp Flaking:** Pass
- ▶ **Material VOC:** 395 grams / Liter (3.2 Lbs/gal)
- ▶ **Non-Volatiles:** 51% min.
- ▶ **Penetration:** BMS 3-23F Pass
- ▶ **Shelf Life:** 3 Years From Date Of Shipment If Properly Stored
- ▶ **Solvent Type:** Aliphatic
- ▶ **Specific Gravity:** 0.90
- ▶ **Water Displacement:** 0% Rust



For more information contact us :  
[zipchem@addevmaterials.com](mailto:zipchem@addevmaterials.com)



Part of



**ADDEV**  
MATERIALS

### COR-BAN® 35 UNDYED



Page 4 of 6

### *Product description:* **CORROSION INHIBITING COMPOUND**

#### **AVAILABLE PACK SIZES:**

##### **Cor-Ban® 35 Undyed**

- ▶ Case of 12 of 16 fl oz (473 mL) Aerosols-006710
- ▶ Case of 12 each Quart (946 mL)-101482
- ▶ 8 oz (227 gram) Brush In Cap-101477
- ▶ Case of 4 each Gallon (4 each of 3.8 Liter) Cans-009410
- ▶ 5 Gallon (18.9 Liter) Pail-006708
- ▶ 55 Gallon (208 Liter) Drum-006709
- ▶ Special Packaging Upon Request

##### **Formit®**

- ▶ 12 Assemblies Per Package
- ▶ **Formit® Sample Pack** with 3 each of  
**Formit®-18-F,**  
**Formit®-18-180,**  
**Formit®-18-360,**  
and **Formit®-18 STD-Fog-100107**



##### **Wet Film Thickness Gauge**

- ▶ 100266



For more information contact us :  
[zipchem@addevmaterials.com](mailto:zipchem@addevmaterials.com)



Part of



**ADDEV**  
MATERIALS



### **COR-BAN® 35 UNDYED**



Page 5 of 6

*Product description:*

### **CORROSION INHIBITING COMPOUND**

#### **AVAILABLE PACK SIZES (CONTINUED FROM PAGE 4):**

##### **Sur-Prep® 3160**

- ▶ Case of 12 of 16 fl oz (473 mL) Aerosols-010938
- ▶ Case of 4 each Gallon (4 each of 3.8 Liter) Cans-008578
- ▶ 5 Gallon (18.9 Liter) Pail-008579
- ▶ 55 Gallon (208 Liter) Drum-008580
- ▶ Case of 6 Canisters of Towelettes-100026
- ▶ Case of 100 Individual Towelettes-011844
- ▶ Special Packaging Upon Request

##### **Sur-Prep® 3167**

- ▶ Case of 12 of 16 fl oz (473 mL) Aerosols-103765
- ▶ Case of 4 each Gallon (4 each of 3.8 Liter) Cans-103762
- ▶ 5 Gallon (18.9 Liter) Pail-103763
- ▶ 55 Gallon (208 Liter) Drum-103764
- ▶ Special Packaging Upon Request

### **COR-BAN® 35 UNDYED**



Page 6 of 6

*Product description:*

### **CORROSION INHIBITING COMPOUND**

#### **AVAILABLE PACK SIZES (CONTINUED FROM PAGE 5):**

##### **Zip-Strip™ 125M**

- ▶ 16 fl oz (473 mL) Aerosol-102614
- ▶ Case of 4 each Gallon (4 each of 3.8 Liter) Cans-102608
- ▶ 5 Gallon (18.9 Liter) Pails-102609
- ▶ 55 Gallon (208 Liter) Drums-102610
- ▶ Special Packaging Upon Request

##### **D-5640NS**

- ▶ Case of 12 of 16 fl oz (473 mL) Aerosols-002070

##### **ZC-640**

- ▶ Case of 4 each Gallon (4 each of 3.8 Liter) Cans-009430
- ▶ 5 Gallon (18.9 Liter) Pail-002155
- ▶ 55 Gallon (208 Liter) Drum-008181
- ▶ Special packaging upon request



For more information contact us :  
[zipchem@addevmaterials.com](mailto:zipchem@addevmaterials.com)



Part of



**ADDEV**  
MATERIALS