



Product description:

SELF HEALING CORROSION CONTROL LUBRICANT

FEATURES:

- A versatile rust preventive coating
- Provides a tough and transparent film that is water displacing for use under the most severe corrosion conditions
- Self healing

KEY BENEFITS:

- Prevents corrosion up to 2 years
- Protects metal substrates from corrosion in severe salt spray environments
- Does not flake
- An extremely effective corrosion preventive for the lubrication of and protection of aircraft cables
- Resists flow up to 175°F (79°C)
- Low toxicity







- Parts that are coated with D-5082NS can be stored outside
- Water displacing for use under the most severe corrosion conditions
- Dry to touch within two hours
- Adheres firmly to metal surfaces
- **D-5082NS** is recommended for aircraft.
- Free of chromates
- Free from heavy metals

Rev: 29089J 12-17-2025









Page 2 of 5

Product description:

SELF HEALING CORROSION CONTROL LUBRICANT

SPECS:

UAL OIL 4501-11SC

APPLICATIONS:

- ✓ Appy in fuselages and wing sections when preparing aircraft for storage or HMV (Heavy Maintenance Visits)
- ✓ One aerosol can will cover approximately 50 ft² (4.6 m²) of area
- ✓ **D-5082NS** can be used in conjunction with the **Formit®** extensions to provide targeted spray to areas that may be difficult to reach but need to be coated. Please refer to the **Formit®** technical data sheet for more information.
- ✓ Bulk application available as ZC-082
- ✓ D-5082NS can be removed using Sur-Prep® 3160, D-5640NS, ZC-640, Sur-Prep® 3167, or mineral spirits.
- ✓ Store **D-5082NS** at 40°F 100°F (4.4°C 37.8°C) in the original unopened containers. Keep containers closed when not in use and protect **D-5082NS** from direct sunlight.







Page 3 of 5

Product description:

SELF HEALING CORROSION CONTROL LUBRICANT

PHYSICAL PROPERTIES:

Density F.: 7.1 Lbs. / Gal. (850 grams/liter)

Film Thickness: 0.9-1.0 mils (23-25 microns)

► Flash Point: Flammable

Pour Point: 100°F (38°C)

Shelf Life: 3 Years From Date Of Shipment If Properly Stored

► Viscosity, Cps @ 80 Deg. F (27 Deg. C).: 100-500

AVAILABLE PACK SIZES:

D-5082NS

Case of 12 of 16 fl oz (473 mL) Aerosols-002054

ZC-082

- Case of 4 each Gallon (4 each of 3.8 Liter) Cans-009424
- 5 Gallon (18.9 Liter) Pails-002131
- ▶ 55 Gallon (208 Liter) Drum-002132
- Special Packaging Upon Request









Page 4 of 5

Product description:

SELF HEALING CORROSION CONTROL LUBRICANT

AVAILABLE PACK SIZES (CONTINUED FROM PAGE 3):

D-5640NS

Case of 12 of 16 fl oz (473 mL) Aerosols-002070

ZC-640

- Case of 4 each Gallon (4 each of 3.8 Liter) Cans-009430
- 5 Gallons (18.9 Liter)-002155
- 55 Gallons (208 Liter)-008181
- Special Packaging Upon Request

Sur-Prep® 3167

- Case of 12 of 16 fl oz (473 mL) Aerosols-103765
- Case of 4 each Gallon (4 each of 3.8 Liter) Cans-103762
- 5 Gallon (18.9 Liter) Pail-103763
- 55 Gallon (208 Liter) Drum-103764
- Special Packaging Upon Request







CORROSION INHIBITING COMPOUNDS

D-5082NS



Page 5 of 5

Product description:

SELF HEALING CORROSION CONTROL LUBRICANT

AVAILABLE PACK SIZES (CONTINUED FROM PAGE 4):

Sur-Prep® 3160

- Case of 12 of 16 fl oz (473 mL) Aerosols-010938
- Case of 4 each Gallon (4 each of 3.8 Liter) Cans-008578
- 5 Gallon (18.9 Liter) Pail-008579
- ▶ 55 Gallon (208 Liter) Drum-008580
- Case of 6 Canisters of Towelettes-100026
- Case of 100 Individual Towelettes-011844
- Special Packaging Upon Request

Formit® 12 Assemblies Per Package Formit® Sample Pack with 3 each of Formit®-18-F, Formit®-18-180, Formit®-18-360, and Formit®-18 STD-Fog-100107

