

SUR-PREP® 3167



Page 1 of 4

Product description:
**CIC REMOVER, HEAVY DUTY
DEGREASER & SURFACE PREP
CLEANER**

FEATURES:

- ▶ A versatile evaporating solvent blend

KEY BENEFITS:

- ▶ Extremely effective on corrosion on a wide range of aviation soils and surfaces, such as corrosion inhibiting compounds (CIC's), MoS₂ grease, hydraulic fluid, wax, and carbon deposits
- ▶ Performs exceptionally well removing aged, multi-layered CIC's
- ▶ Does not leave a residue
- ▶ Removes heavy aged CIC coatings
- ▶ Penetrates to remove soil and greases
- ▶ **Sur-Prep® 3167** used on all types of materials and surfaces
- ▶ Dries completely
- ▶ Prepares and cleans critical surfaces prior to painting and bonding
- ▶ Broad solvency range



SPECS:

- Airbus AIMS 09-03-000
- Boeing D6-17487
- Boeing BSS 7432
- Cessna SPM 51-30-10: CIC Remover (TMDA20230018)

Rev: 290781
05-11-2026

SUR-PREP® 3167



Page 2 of 4

Product description:
**CIC REMOVER, HEAVY DUTY
DEGREASER & SURFACE PREP
CLEANER**

APPLICATIONS:

- ✓ Apply **Sur-Prep® 3167** to the surface to be cleaned or prepared for painting/bonding
- ✓ Apply by wipe or spray
- ✓ The **Sur-Prep® 3167** aerosol can be used in conjunction with the **Formit®** extensions to provide targeted spray to areas that may be difficult to reach but need to be cleaned. Please refer to the **Formit®** technical data sheet for more information. The **Sur-Prep® 3167** aerosol can also be used with the **Zip-Chem® Aerosol Trigger Sprayer** which is designed for use with any **Zip-Chem®** aerosol can.
- ✓ Ideal for mixed fleet carriers and MRO maintenance operations.
- ✓ Refer to the **Sur-Prep® 3167** application manual for detailed application instructions. This manual can be obtained by asking your **Zip-Chem®** sales rep for a copy of this document.
- ✓ **Sur-Prep® 3167** should be stored at **40°F to 100°F (4.4°C - 37.8°C)** in the original unopened containers. Keep containers closed when not in use and protect **Sur-Prep® 3167** from direct sunlight.

PHYSICAL PROPERTIES:

- ▶ **Boiling Point (°C):** 116 (240°F)
- ▶ **Composite Vapor Pressure:** 0.9 mm of Hg
- ▶ **Density (g/cm, 25°C (77°F)):** 0.90
- ▶ **Evaporation Rate(Xylene=1):** 1.7
- ▶ **Flash Point (°C):** 32 (90°F)

SUR-PREP® 3167



Page 3 of 4

Product description:
**CIC REMOVER, HEAVY DUTY
DEGREASER & SURFACE PREP
CLEANER**


PHYSICAL PROPERTIES (CONTINUED FROM PAGE 2):

- ▶ **Hydrogen Embrittlement:** Pass
- ▶ **Paint Softening (ASTM F-502):** Does not soften
- ▶ **Shelf Life:** 3 Years From Date Of Shipment If Properly Stored
- ▶ **Surface Tension (Dynes/cm):** 22

AVAILABLE PACK SIZES:

Sur-Prep® 3167

- ▶ Case of 12 of 16 fl oz (473 mL) Aerosols-103765
- ▶ Case of 4 each Gallon (4 each of 4.8 Liter) Cans-103762
- ▶ 5 Gallon (18.9 Liter) Pail-103763
- ▶ 55 Gallon (208 Liter) Drum-103764
- ▶ Special Packaging Upon Request





Sur-Prep®

SURFACE PREPARATION & AVIONICS CLEANERS

SUR-PREP® 3167




Page 4 of 4

Product description:
**CIC REMOVER, HEAVY DUTY
DEGREASER & SURFACE PREP
CLEANER**

AVAILABLE PACK SIZES (CONTINUED FROM PAGE 3):

Formit®

- ▶ 12 Assemblies Per Package
- ▶ **Formit® Sample Pack** with 3 each of
Formit®-18-F,
Formit®-18-180,
Formit®-18-360,
and **Formit®-18 STD-Fog-100107**



Zip-Chem® Aerosol Trigger Sprayer

- ▶ 010040